

Page 1/2

# NoriCure® TFL

# UV Curing Screen Printing Primer for Thermal Transfer Printing

## **Area of Application**

NoriCure® TFL is a UV curing screen printing primer suitable for printing on PC, PVC, PETG, ABS and Paper.

#### Mesh

Polyester fabrics of 150 to 180 threads/cm (380 to 460 threads/inch) are suitable.

#### **Stencil**

UV ink and solvent resistant emulsions must be used. Excellent results during long production runs are achieved by using Pröll Diazo-UV-Polymer Emulsion Norikop 10 HQ.

# Squeegee

All commercially available squeegees with an average hardness of 75° up to 80° Shore A.

#### **UV** Curing

Guideline: For curing NoriCure® TFL layers which were printed with a mesh 150-31 Y (380 threads/inch), a UV dose (Kühnast UV-Integrator, spectral range: UV 250 – 410 nm, max. 365 nm) of approx. 150 mJ/cm² is necessary.

The UV dose for sufficient curing depends on ink layer thickness (printing mesh) as well as the type and color of the substrate. Depending on such parameters the dose must be adjusted.

# **Processing**

NoriCure® TFL may only be processed in areas without UV light prior to UV curing. Invisible UV rays from sunlight as well as UV rays from artificial light sources (e.g. fluorescent lamps) have to be avoided.

Necessary equipment is available from EncapSulite® International Inc., Rosenberg, Texas or EncapSulite European Office, Cologne, Germany. Making use of the following UV blocking products is especially recommended:

- UV-Stop Security Fluorescent Tubes, trade name "UV-Shrinkwrap Tube / Type C20" (clear), cut off point at 400 nm
- UV absorbing sleeves, trade name "UV-Safety Sleeve / Type C20 clear", cut off point at 400 nm
- UV filter film, available in rolls for window application, trade name "EncapSulite UV-Filter C10"
- Further information can be found on www.encapsulite.com or www.encapsulite-europe.com

## **Cleaning of Screens and Utensils**

UNI-REIN A III or UNI-CLEANER FP61

# **Shelf Life**

The shelf life stated on the label assures the product's quality and refers to unopened original cans stored in a dry place at temperatures between 5 °C (40 °F) and 25 °C (75 °F).

Proell GmbHTreuchtlinger Str. 29Phone +49 9141 906-0info@proell.de91781 Weissenburg / GermanyFax +49 9141 906-49www.proell.de

#### NoriCure® TFL

## **Safety Precautions**

UV inks which have not been cured may have an irritating and sensitizing effect to the skin and may cause allergic, hypersensitive reactions. Please use an accurate and clean working method when processing UV inks. You should wear suitable personal protection equipment (gloves, safety goggles, working clothes)!

Uncured sheets are considered special waste and should therefore be cured under UV light before disposal. Please pay attention to the respective safety data sheets.

#### **Important**

Allow the product to adjust to ambient temperature in the closed container before use.

Printing results, to a large extent, depend on the substrate as well as the printing and application conditions. We recommend checking your printing materials under your conditions of use prior to any production runs. Materials that are supposed to be identical may vary from manufacturer to manufacturer and even from batch to batch. Some substrates and printing inks may have been treated with or contain sliding agents, antistatics or other additives which will impair the adhesion of the primer.

The curing of UV systems is influenced by the output and the emission spectrum of the UV bulb, thus affecting the adhesion of the cured ink film.

The information contained in the technical information/instruction sheets or other product information sheets is based on product testing conducted by Pröll. Because printing and environmental factors critically affect each individual ink application, the above mentioned information and instructions represent only general recommendations concerning product characteristics and directions for use and should not be construed as representing express warranties regarding the product. The information and instructions in no way release the purchaser from his obligation to verify and test the inks and their application for the specific request, regarding: product characteristics, weather resistance, mixing proportions, gloss, thinning, special mixtures, printability, drying speed, cleaning, effects on or of other materials to be contacted and safety precautions. All details contained in the instruction sheet "General Information on Screen Printing Inks" are to be considered. The further manufacture and use of products containing our inks by the purchaser takes place beyond our control, and the responsibility for further application and use of our product resides solely with the purchaser. Pröll disclaims any warranties, express or implied.

This information supersedes all previous technical information.