



# NORIPHAN® PCI N

Halogen Free Process Screen Printing Ink for the IMD/FIM Technology (back molding of screen printed films)

Press-ready

## Area of Application

**NORIPHAN® PCI N is a solvent-based one-component process screen printing ink based on a high temperature resistant thermoplastic resin.**

## Films

**PC film:** Makrofol®<sup>1</sup>  
**PC blend film:** Bayfol®<sup>1</sup>

## Color Shades

*HF = halogen free*

<b>Halogen Free Process Colors</b>	156 Process Yellow HF	949 Process Black HF
	357 Process Magenta HF	099 Process Paste HF
	558 Process Cyan HF	<i>to brighten up process colors</i>
<b>Halogen Free Special Colors</b>	945 White Opaque HF <i>for fine details</i>	955 Black Opaque HF <i>for fine details</i>

## Mesh

For process printing polyester fabrics of 150 – 180 threads/cm (380 – 460 threads/inch) are recommended.

## Stencil

Solvent resistant emulsions must be used. Excellent results during long production runs are achieved by using Pröll Diazo-UV-Polymer Emulsion Norikop 10 HQ.

## Auxiliary

### Thinner

Thinner S 408 (*halogen free*)

### Overprinting

NORIPHAN® PCI N can be overprinted with NORIPHAN® HTR N inks.

### Cleaning of Screens and Utensils

UNI-REIN A III

### Drying

NORIPHAN® PCI N is a physically curing ink system which dries through evaporation of the solvent in a tunnel dryer.

#### Note:

To protect PC films from extensive solvent attack, tunnel dryers should be used also for small trial runs. Rack drying is not recommended (cracking!).

<sup>1</sup> Makrofol® and Bayfol® are registered trade marks used by Covestro AG, Germany

# NORIPHAN® PCI N

## Conditioning / Post-curing

Complete evaporation of solvent residues in ink and film is necessary for further processing of printed films in the IMD/FIM process.

Thinner residues can lead to washout during the back molding process, or damage during the climatic test or use of the end product.

Fully benefiting from NORIPHAN® PCI N's superior properties (adhesion, suitability for back molding, etc.) requires guaranteeing an absolute minimum of solvent residues.

Post-curing is done after printing the last ink layer; the ideal conditions for each product must be determined individually.

For best results, dry separately on a rack in a well ventilated box oven with air exchange.

### Conditions:

Post-curing at 75 – 90 °C (165 – 195 °F) for 1 – 5 hours.

Maximum temperature 70 – 80 °C (160 – 175 °F) for processing heat sensitive films of PC blends such as Bayfol® CR.

In case of an application of too high temperatures with Bayfol® CR a change into bluish coloring of the film could be observed.

## Bonding Strength

For good adhesion, at least **2 fully covering layers of NORIPHAN® PCI N** should be printed. The first layer can be composed of almost fully covering graphic motifs.

## Safety Precautions

NORIPHAN® PCI N inks are inflammable. Smoking or open flames are strictly prohibited during use of these products.

Processing NORIPHAN® PCI N inks requires normal hygiene in the workplace.

Please see recommendations on label and read the material safety data sheets before use.

## Shelf Life

The shelf life stated on the label assures the ink's quality and refers to unopened original cans stored in a dry place at temperatures between 5 °C (40 °F) and 25 °C (75 °F).

## Important

Allow the ink as well as all the auxiliaries to be added to adjust to ambient temperature in the closed container before use.

Printing results, to a large extent, depend on the substrate as well as the printing and application conditions. We recommend checking your printing materials under your conditions of use prior to any production runs. Materials that are supposed to be identical may vary from manufacturer to manufacturer and even from batch to batch. Some substrates may have been treated with or can contain sliding agents, antistatics or other additives which will impair the adhesion of the inks.

For further information concerning printing as well as tips on drying, forming and injection molding the corresponding Technical Information NORIPHAN® HTR N is also basically valid.

It is not always possible to produce a given part using IMD/FIM technology.

The resins used for back molding IMD/FIM ink systems are supplied as commercial technical products. They are different in chemical composition as well as the content of additives. Process parameters will also influence the quality of the finished IMD/FIM parts.

Before starting a production run, it is necessary to test samples of each newly designed part systematically with regard to the specifications for the intended use (e.g. climatic chamber, resistance, etc.).

The information contained in the technical information/instruction sheets or other product information sheets is based on product testing conducted by Pröll. Because printing and environmental factors critically affect each individual ink application, the above mentioned information and instructions represent only general recommendations concerning product characteristics and directions for use and should not be construed as representing express warranties regarding the product. The information and instructions in no way release the purchaser from his obligation to verify and test the inks and their application for the specific request, regarding: product characteristics, weather resistance, mixing proportions, gloss, thinning, special mixtures, printability, drying speed, cleaning, effects on or of other materials to be contacted and safety precautions. All details contained in the instruction sheet "General Information on Screen Printing Inks" are to be considered. The further manufacture and use of products containing our inks by the purchaser takes place beyond our control, and the responsibility for further application and use of our product resides solely with the purchaser. Pröll disclaims any warranties, express or implied.

This information supersedes all previous technical information.